

PrintTex® Blackout I

Fields of application

.02 .04 .05 .07 .08

Specifications

	599171 100
	100 % polyester blackout
	ca. 155/ 310 cm ca. 61/ 122 inch other widths available on request
	B-s1, d0 DIN EN 13501-1
	ca. 290 g/m ² ca. 8.6 oz/yd ²
	ca. 0.41 mm ca. 410 µm
	rolls 50 m 55 yd
	100 Pa: 10.8 l/(m ² s) 200 Pa: 23.1 l/(m ² s) DIN EN ISO 9237
	blank: 6 DIN EN ISO 105-B02
	blank: 0.0 % DIN EN 410
	blank: 0.0 % DIN EN 410
	blank: 88.72 DIN 5033-1
	cold, ultrasonic cut

	length: 0.8 % cross: 0.5 % DIN EN 14704-1
	length: 27.9 N cross: 16.2 N DIN EN ISO 9073-4
	length: 434.8 N cross: 974.5 N DIN EN ISO 13934-1
	length: 38.1 % cross: 45.8 % DIN EN ISO 13934-1

Printing methods

print	UV	Latex	Dyesub
Inside	•	•	
Outside	•	•	

Certifications

Certified for HP Latex Inks	Dry rubbing	4
		ISO 105-X12



PrintTex® Blackout I

Fields of application

.02 .04 .05 .07 .08



Ref.-Nr.: 599171 100 | Preview print sample



PONGS Technical Textiles GmbH

Bahnhofstraße 21
07919 Pausa-Mühltröf
Germany

Phone +49 36645 350-0
salestt@pongs.de
www.pongs.com

We reserve the right for technical modifications.
The above mentioned details are non-binding.
A tolerance of $\pm 5\%$ is valid. Effective: 2019/05