

## PRODUCT DATA SHEET

010 00306

**PRODUCT DESCRIPTION:** Flexible Magnetic Sheeting with matte white PVC film

**STANDARD THICKNESS:** 0.6mm (+/- 0.03mm)

**STANDARD WIDTH:** 1.020mm (+5mm/-1)

**STANDARD LENGTH:** 20M (+0.5M/-0)

**GROSS WEIGHT:** 42,35 KG

### MAGNETIC PROPERTIES

Maximum Energy Product: 0.55 – 0.65 MGOe

Remanence: 1600 – 1900 G

Coercivity: 1200 – 1500 Oe

Intrinsic coercivity: 2200 – 2500 Oe

Pole width: 2.0 mm

Magnetic pull: 24 g/cm<sup>2</sup>

### PHYSICAL PROPERTIES

Flexibility: can be wrapped around a rod with a 12mm radius at 20°C without cracking

Specific Gravity: 3.5 to 3.7 g/cm<sup>3</sup>

Cutting: Scissor cutting, knife-cutting, die-cutting and slitting can be done with ease

### TEMPERATURE RESISTANCE

End-use temperature range: - 30°C / + 55°C

Short term resistance: + 65°C

### MATERIAL PROPERTIES

The magnetic sheeting has a UV hardened coating on the magnetic side

### PVC FILM

The outdoor durability is two years under Middle European conditions. Exposure to severe humidity, UV light and/or conditions found in (sub)tropical or desert regions will cause a more rapid deterioration.

### Suitable for printing with:

Screen	●	Litho/Offset	●
Flexo	tbc	Thermal/Toner-based	○
Latex	tbc	(eco)Solvent	●
UV-Cured	●	Digital/Offset	●
Waterbased / Dye	○	Pigment	○

Legend: ●=good // ●=average // ○=not advisable

**Storage:**

The material should be stored horizontally. Avoid sunlight and keep temperature between 10 and 30 degrees Celcius.

Sanders Group:

Industriepark 3

5663 PG

Geldrop

The Netherlands

[www.sandersgroup.eu](http://www.sandersgroup.eu)

Magnetic Solutions Ltd.

Unit 15c Tinsley Industrial Estate

Shepcote Lane

Sheffield

S9 1TH

United Kingdom

[www.magnetic-solutions-ltd.co.uk](http://www.magnetic-solutions-ltd.co.uk)

Aiman GZ

Parque Empresarial Neinor Henares

Edificio 7 – Nave 14

28880

Meco – Madrid

Spain

[www.aimangz.es](http://www.aimangz.es)